

Flashbay Electronics
Building2, Jixun Industrial Park, Xinjiao, Dong'ao Village,
Shatian Town, Huiyang District, Huizhou City,
Guangdong Province, P.R. China

**DEKRA Testing and Certification (Shanghai)
Ltd., Guangzhou branch**
Block 5, No.3, Qiyun Road, Huangpu District,
Guangzhou, Guangdong, Chin
Tel.: +86 20 6661 2000
Fax: +86 20 6661 2001

Contact
Devin Ai
Tel.: +86 20 6684 3294
E-Mail: devin.ai@dekra.com
Page 1 of 6

TEST REPORT

Test Report No. : **4396992.59** Version 2 (Supersedes Version 1)
Project No. : **4396992.00**
Test Report Date : **2022-12-20**

Job No. : 22-03751

Applicant : Flashbay Electronics
Building2, Jixun Industrial Park, Xinjiao, Dong'ao Village, Shatian Town,
Huiyang District, Huizhou City, Guangdong Province, P.R. China

Product Name : Water Bottles

Model No. : Nova/NV

Test Requested : 1. U.S. 21 CFR F.D.A. Regulation Part 177.1520 Clause 1.1a and 1.1b for polypropylene.
2. U.S. 21 CFR F.D.A. Regulation Part 177.2600 rubber articles intended for repeated use, Section (e) and (f)
3. FDA General Recognized as Safe (GRAS)


Test Method : Please refer to next pages

Sample Received : 2022-11-18 and 2022-11-23

Testing Period : 2022-11-18 to 2022-12-20

Test Results
- following pages -

Resume:

No.	Parameter	Conclusion
		
1.	Test for F.D.A. Regulation on polypropylene 21 CFR 177.1520	PASS
2.	Test for F.D.A. Regulation on Rubber 21 CFR Part 177.2600	PASS
3.	FDA General Recognized as Safe (GRAS)	PASS

Guangzhou, December 20, 2022

Signed for and on behalf of

DEKRA Testing and Certification (Shanghai) Ltd., Guangzhou branch

Chemical & Mechanical





Devin Ai
Laboratory Manager

Attention: Please note that every statement made in this report is only valid for the samples tested and reported herein. This report shall not be reproduced except in full, without the written approval of the testing laboratory.

Sample Descriptions:

No.	Sample Descriptions	Materials (claimed by applicant)
(1)	Lid	PP (Black)
(2)	Body	Stainless steel
(3)	Sealing ring	Silicone (White)

Sample photos:



TEST RESULTS

1. U.S. 21 CFR F.D.A. Regulation Part 177.1520 Clause 1.1a and 1.1b for polypropylene

With reference to the U.S. Food and Drug Administration 21 CFR Part 177.1520 Clause 1.1a and 1.1b.

	Parameter	Result	MDL	Limit
		(1)		
a)	Density	0.904	--	0.880-0.913
b)	Melting Point (°C)	170.1	--	160-180 (1.1a) 150-180 (1.1b)
c)	Maximum extractable fraction in n-hexane, % (w/w)	< 0.5	0.5	6.4
d)	Maximum extractable fraction in xylene, % (w/w)	0.95	0.5	9.8

Remark:

1. % = Percentage
2. MDL = Method Detection Limit

2. U.S. 21 CFR F.D.A. Regulation Part 177.2600 rubber articles intended for repeated use, Section (e) and (f)

With reference to the U.S. Food and Drug Administration 21 CFR Part 177.2600 - rubber articles intended for repeated use, Section (e) and (f).

	Parameter	Test condition	Result (mg/in ²)	MDL (mg/in ²)	Limit (mg/in ²)
			(3)		
(a)	Total extractives in water	Reflux temperature, first 7 hours	<0.20	0.20	20
		Reflux temperature, succeeding 2 hours	<0.20	0.20	1
(b)	Total extractives in n-hexane	Reflux temperature, first 7 hours	5.02	0.20	175
		Reflux temperature, succeeding 2 hours	<0.20	0.20	4

Remark:

1. mg/in² = Milligram per square inch

3. FDA General Recognized as Safe (GRAS)**Total Chromium content**

By acid digestion followed by Inductively Coupled Plasma Emission Spectroscopic analysis.

Parameter	Result (%)	MDL (%)	Limit (%)
	(2)		
Tot. Chromium (Cr)	17.60	0.005	16 Min.

Remark:

1. MDL = Method Detection Limit

Remark:

The information of Annex was submitted by the client. DEKRA Testing and Certification (Shanghai) Ltd., Guangzhou branch takes no responsibility for any mistake caused by inaccuracy and/or invalid information.

Annex 1



---End of Report---